

ALPHA® EcoSol Solder Alloy

Low Melt Point, Pb-Free Solder Alloy for PV Ribbon

DESCRIPTION

From the world's leading manufacturer of electronic grade solder materials comes ALPHA EcoSol, the industry's first Low Melt Point, Pb-free Solder Alloy designed specifically for PV Ribbon Tinning and cSi Module Assembly. ALPHA EcoSol is also low cost, priced well below conventional Pb-free solders, closer to the price of standard Sn60Pb40 solder. The low melt point means it has a liquidus temperature near Sn60Pb40 and above conventional lamination temperatures. It can generally be "dropped in" to most current assembly processes. ALPHA EcoSol has mechanical, electrical and thermal conductivity properties considered acceptable to PV Module Assemblers and passes IEC-61215 and 61730 reliability requirements.

FEATURES & BENEFITS

Features:

- Low Cost – Over 30% below the price of most other Pb-Free alloys
- Low Melt Point relative to other popular Pb-free alloys
- Exhibits Mechanical Reliability, Soldering and Electrical Conductivity performance deemed acceptable to PV Module Assemblers and Industry Standards (IEC-61215 and 61730)

Benefits:

- Low price supports transitioning to Pb-free without incurring substantially higher solder costs
- Has a liquidus temperature near Sn60Pb40 solder and above conventional lamination temperatures. This, combined with excellent wetting characteristics, means ALPHA EcoSol can generally be "dropped in" to most current cSi module assembly processes with no change in throughput.
- High mechanical strength ensures long module service life
- High conductivity means no module power loss after transitioning to ALPHA EcoSol

APPLICATION

ALPHA EcoSol is designed to be used as a solder coating over a copper core to make the PV Ribbon that is used in cSi solar module assembly. With a liquidus temperature of ~179°C and excellent soldering characteristics, ALPHA EcoSol can be used as a "drop-in" replacement for many of the popular Pb bearing alloys used today (ie. Sn60Pb40, Sn62Pb38Ag2, etc...). A solder pot temperature of ≥235°C is recommended for tinning of the copper. In its molten state, ALPHA EcoSol has been found to wet to a clean copper ribbon at the same rate as other popular alloys in high speed dipping / tinning processes. It forms a strong intermetallic bond to copper and ultimately to the Ag busbar of the solar cell ensuring a highly reliable and electrically conductive connection. Alpha EcoSol can be plated at different thicknesses depending on the requirement and forms a clean and uniform surface finish that resists corrosion and oxidation after exposure to common fluxes and during the normal service life of the solar module.

ALPHA[®] EcoSol Solder Alloy

Low Melt Point, Pb-Free Solder Alloy for PV Ribbon

TECHNICAL DATA

Complies with all requirements of RoHS Directive (Article 4.1 of the European Directive 2011/65/EU). Alloy specification for Maximum Lead (Pb) Content = **0.05%**

Material Property	Units	EcoSol
Liquidus	Celsius	179.7
Hardness	HV	23
Density	g/cm ³	8.14
Specific Heat Capacity	J/gK	0.174
Thermal Diffusivity	mm ² /s	20.2
Tensile Strength	MPa	240.5
Tensile Strain	%	6.5
Yield Strength	MPa	69.3
Elongation	%	29
Wetting Speed	t ₀ (sec)	1.15
Wetting Force	F _{max} (m)	4.3
JIS Spread Testing	S _R %	73.5
Copper Erosion Rate	Time (min)	16.5*
Silver Erosion Rate	Time (sec)	28**

*This is an indication of how fast the molten solder may erode copper during the PV ribbon tinning process. 2x better than silver (Ag) bearing Pb-free alloys

**This is an indication of how fast PV ribbon coated with Alpha EcoSol may consume the silver plated busbar during the tabbing and stringing process.

SAFETY

Consult the SDS for safety information. The most recent version of the SDS is available from alphaassembly.com.

STORAGE

Store the solder bar in a cool, dry, and non-corrosive environment. Wrap up the solder bar when not in use to reduce exposure to environment.

ALPHA® EcoSol Solder Alloy

Low Melt Point, Pb-Free Solder Alloy for PV Ribbon

AVAILABILITY

Alpha EcoSol is available worldwide in Bars, Ingots, and Chunks.

CONTACT INFORMATION

To confirm this is the most recent issue, please contact Alpha Assembly Solutions

AlphaAssembly.com

<p>North America 300 Atrium Drive Somerset, NJ 08873, USA 800.367.5460</p>	<p>Europe Unit 2, Genesis Business Park Albert Drive Woking, Surrey, GU21 5RW, UK 01483.758400</p>	<p>Asia 8/F., Paul Y. Centre 51 Hung To Road Kwun Tong, Kowloon, Hong Kong 852.3190.3100</p>
-----------------------------------------------------------------------------------------------	---------------------------------------------------------------------------------------------------------------------------	---------------------------------------------------------------------------------------------------------------------

Also read carefully warning and safety information on the Safety Data Sheet. This data sheet contains technical information required for safe and economical operation of this product. READ IT THOROUGHLY PRIOR TO PRODUCT USE. Emergency directory assistance Chemtrec 1 - 800 - 424 - 9300.

DISCLAIMER: All statements, technical information and recommendations contained herein are based on tests we believe to be reliable, but the accuracy or completeness thereof is not guaranteed. No statement or recommendation shall constitute a representation unless set forth in an agreement signed by officers of seller and manufacturer. NO WARRANTY OR MERCHANTABILITY OR WARRANTY OF FITNESS FOR A PARTICULAR PURPOSE IS MADE. The following warranty is made in lieu of such warranties and all other warranties, express, implied, or statutory. Products are warranted to be free from defects in material and workmanship at the time sold. The sole obligation of seller and manufacturer under this warranty shall be to replace any product defective at the time sold. Under no circumstances shall manufacturer or seller be liable for any loss, damage or expense, direct or consequential, arising out of the inability to use the product. Notwithstanding the foregoing, if products are supplied in response to a customer request that specifies operating parameters beyond those stated above, or if products are used under conditions exceeding said parameters, the customer by acceptance or use thereof assumes all risk of product failure and of all direct, indirect and consequential damages that may result from use of the products under conditions, and agrees to exonerate, indemnify and hold harmless MacDermid Incorporated therefrom. No suggestion for product use nor anything contained herein shall be construed as a recommendation to use any product in infringement of any patent rights, and seller and manufacturer assume no responsibility or liability for any such infringement.

© Registered Trademark of MacDermid Performance Solutions. ™ Trademark of MacDermid Performance Solutions.
© Platform Specialty Products Corporation and its subsidiaries 2016.